



PROHESIVE™ PRO PREMIUM



PROHESIVE™ PRO PREMIUM is a premium quality, extremely high strength, polymer modified, flexible cement based adhesive, developed to bond most types of tiles. Its unique formula makes it easy to mix and apply. Suitable for most internal and external applications including tile on tile and green screeds and immersed applications, it can be used in both internal and external, floor and wall tile installations.

PRODUCT FEATURES

- C2 – High bond strength
- E – Extended open time
- S1 – Good flexibility
- White
- Self priming
- Water washable
- Suitable for areas where thermal movement is anticipated
- ≤ 0.9mm crack bridging capability
- Low VOC

SUITABLE TILE TYPES

- Terracotta
- Ceramic
- Porcelain
- Natural Stone: inc marble, granite, limestone & travertine
- Glass mosaics

AREAS OF USE

- Interior & exterior applications
- Walls & floors • Concrete
- Green screeds and render
- Sand / cement screeds • Cement render
- Fibrous cement sheeting
- Compressed fibrous cement sheeting
- Plasterboard
- Tiling over CTA™ certified waterproofing membranes
- Existing tiles • Swimming pools
- Eco Silent acoustic mat

SURFACE PREPARATION

General

Ensure that the surface is dry and clean. Remove any loose material and all contaminants such as grease, oil and dust prior to applying. Make certain that there are no undulations in the surface that may require PROHESIVE™ PRO PREMIUM to be applied at a thickness in excess of 10mm. If necessary level floors using ECO SYSTEMS™ ECO LEVEL self levelling underlayment.

No water absorbed	Mechanically prepare the surface / Use Eco Prep n Prime
Moderate water absorbed	Clean with a damp sponge and fresh water
All water absorbed	Broom on liberal amounts of water

This simple indicative test is performed after vacuuming or sweeping a number of test areas and applying a single drop of fresh drinking water from the end of your finger. This should be approximately 10 to 20mm wide when it first hits the floor – if it beads and remains whole then “No water is absorbed”. If it loses all gloss within 20 to 60 seconds then “Moderate water is absorbed”. If the gloss disappears instantly or within 20 seconds then the substrate has “All water absorbed”. Look for different surface appearances in your floor and test each to ensure your test is representative of the whole area. Perform test in both a cool shaded area and an exposed sunny area if tiling externally.

SUBSTRATES / BACKGROUNDS

Concrete Floors

Allow at least 7 days for the concrete to cure. A flexible adhesive is recommended for installations over post tensioned and suspended concrete slabs. Concrete should be left with an open surface – standard helicopter finishes are generally acceptable if they display the “Moderate water absorption” in the substrate test. Wood float or broom finish is preferred where possible. All traces of curing compounds (or sealers) should be removed prior to tiling as these can act as release agents. The surface should be flat and even unless falls are incorporated where required.

Sand / Cement Screeds and Renders

The screeds and / or renders must conform with the appropriate standard and should be left with a wood float finish and left to cure for at least 24 hours per 25mm thickness.

Sheet Walls

Plasterboard and fibrous cement sheeting must be solidly fixed in accordance with the manufacturer's instructions specifically for tiling and should be wiped with a damp sponge prior to tiling particularly where a jointing compound has been used.

Compressed Fibrous Cement Sheeting

Boards must be solidly fixed in accordance with manufacturer's instructions specifically for tiling and should be wiped with a damp sponge prior to tiling.

Existing Tiles

Any existing tiles must be well bonded and be free from any sealers or coatings. It may be necessary to mechanically prepare the area to be tiled. Dense, low absorbent surfaces may be coated with ECO SYSTEMSTM ECO PREP'N'PRIME prior to tiling. Contact CTATM for further advice.

CTATM Certified Waterproofing Membranes

Waterproofing membranes must be allowed to cure as per the product's specification.

MIXING

Pour room temperature, potable water into a clean mixing container before slowly adding the adhesive powder. A 20kg bag of PROHESIVETM PRO PREMIUM will require approximately 5.0 – 5.5 litres of water. Always add powder to the water and mix until a smooth toothpaste consistency is achieved. Allow mixture to stand for 5 minutes to allow the chemicals to slake, then restir and the product is ready for immediate use. DO NOT ADD MORE WATER. Restirring may be necessary during the pot life of the product.

APPLYING

- Tiles should be fixed in accordance with Australian Standard AS3958.1 – 2007.
- Ensure the back of each tile is clean and free from dust or other contaminants. The adhesive should be applied in areas not exceeding one square metre at a time to ensure the adhesive does not skin prior to fixing. Notch the adhesive with the correct sized trowel in a straight line avoiding swirls.
- While pressing the tiles into the adhesive, slide them at 90 degrees to the direction of the notches for about the distance of the notch; i.e. 10mm for the 10mm notched trowel. This ensures that the whole back of the tile is in contact with the adhesive.
- It is advisable to remove tiles regularly to check that the whole of the back of the tile has maximum coverage as per the Standard. Contact CTATM if you are unsure of the requirements. Large format tiles may require “back-buttering” to ensure full adhesive contact with the back of the tile.
- All adhesive residue must be removed from the face of tiles, joints and fittings before the adhesive sets.

OPEN TIME

30 minutes at 23°C and 60% relative humidity.

POT LIFE

3.5 hours at 23°C and 60% relative humidity.

CURING

Tiles can accept foot traffic and may be grouted after 24 hours. This is dependent on the density of the background and tiles and the ambient temperature and humidity.

GROUTING

Tiles should be grouted using the appropriate POLYBLENDTM premium grout. Select colour and range to suit joint width and preferred finish.

CLEANING

Tools and equipment can be washed using clean water before the adhesive has set.

INCORPORATING MOVEMENT JOINTS

Movement Joints must be installed according to Australian Standard AS3958.1 – 2007.

COVERAGE

Notched Trowel Size	Coverage Per 20Kg Bag
6mm	12m ²
12mm	8 m ²

STORING

When PROHESIVETM PRO PREMIUM is stored in its original unopened package in a dry area at a temperature of 23°C and a relative humidity of 60%, it should be usable for approximately 12 months.

HANDLING

CTATM supports best practice in material handling: Gloves, mask and protective clothing should be worn. For further information refer to product SAFETY DATA SHEET.

PACK SIZE

Available in 20kg paper bags

LIMITATIONS

- PROHESIVETM PRO PREMIUM cannot be used directly over tongue and grooved timber flooring, particleboard, medium density fibreboard or masonite.
- PROHESIVETM PRO PREMIUM is not suitable for use with moisture sensitive tiles or stone.
- PROHESIVETM PRO PREMIUM must not be used directly over solvent based polyurethane waterproofing membranes.
- PROHESIVETM PRO PREMIUM can only be used over high quality water based waterproofing membranes that have been certified by CTATM
- Special fixing techniques are required when tiling externally at heights that exceed 2.7 metres.
- The performance of PROHESIVETM PRO PREMIUM will be compromised when tiling in temperatures below 5°C and above 35°C.
- Contact CTATM for advice if further information is required.

WARRANTY

Construction Technologies Australia Pty Ltd (CTATM) warrants its products for a period of twelve (12) years from the date of sale. Visit www.ctaust.com.au to view the full terms and conditions of this warranty.

FOR FURTHER INFORMATION REFER TO SAFETY DATA SHEET. EMERGENCY NUMBER. 1800 033 111 (AUST)

NEW SOUTH WALES
2 Prime Drive
Seven Hills NSW 2147
t 02 9674 1004 f 02 9674 2002

VICTORIA / TAS
33 Fiveways Boulevard
Keysborough VIC 3173
t 03 9797 0600 f 03 9797 0666

WESTERN AUSTRALIA
61 Bushland Ridge
Bibra Lake WA 6155
t 08 9456 3655 f 08 9456 3644

QUEENSLAND
70 Parker Court Pinkenba QLD 4008
t 07 3633 9222 f 07 3633 8200

SOUTH AUSTRALIA / NT
28 Kenworth Road Gepps Cross SA 5094
t 08 8162 9055 f 08 8162 9099

NEW ZEALAND
85-91 Patiki Road
Avondale Auckland 1026
t 0800 745 269 f 0800 745 232