



# Admix-B



**MCB<sup>TM</sup> ADMIX-B** is a modified dispersion of Styrene Butadiene Copolymer emulsion, which can be used as an admixture for cement mortars used for screeding, rendering, bricklaying, pointing and repairs. **MCB<sup>TM</sup> ADMIX-B** improves adhesion, durability, flexibility, abrasion resistance and workability of modified cement mortars. **MCB<sup>TM</sup> ADMIX-B** is a water resistant, multipurpose admixture and is recommended for use in internal, external and wall & floor applications.

## PRODUCT FEATURES

- Reduces porosity
- Improves flexibility and strength
- Reduces shrinkage and cracking
- Improves adhesion and abrasion resistance
- Suitable for internal and external applications
- Extends open time and workability
- Easy application

## AREAS OF USE

- Porous concrete
- Cement render
- Blockwork
- Brickwork
- Light weight blocks
- Sand/cement screeds

## SURFACE PREPARATION

### General

Ensure that the surface is dry and clean. Remove any loose material and all contaminants such as grease, oil and dust prior to applying. Allow at least 7 days for the concrete to cure. Concrete should be left with an open surface standard helicopter finishes are generally acceptable if they display the "Moderate water absorption" in the substrate test. Wood float or broom finish is preferred where possible. All traces of curing compounds (or sealers) should be removed prior as these can act as release agents. The substrate must be pre-wetted (dampened) with clean water.

## MIXING

**MCB<sup>TM</sup> ADMIX-B** should be stirred before use.

### Slurry Bond Coat

Mix 1 part **MCB<sup>TM</sup> ADMIX-B** with 1 part clean water and 2 parts Portland cement by volume and mix thoroughly to produce a brushable consistency, apply this mixture to the dampened masonry substrate using a stiff bristle broom or brush ensuring mix is worked well into the substrate. Apply subsequent topping while the slurry bond coat is still wet and tacky.

PROCRETE	WATER	CEMENT
1 Part	1 Part	2 Parts

### Sand/Cement Screeds and Renders

**MCB<sup>TM</sup> ADMIX-B** may be used as a mortar additive. Premix 1 part **MCB<sup>TM</sup> ADMIX-B** with 2 parts clean water, use this premix as the gauging water to mix sand and cement screed and/or render, a semi dry consistency is recommended, adjust mix to suit. Apply the mix to the desired thickness. The screeds and/or renders must conform with the appropriate standard and should be left with a wood float finish and left to cure for at least 24 hours per 25mm thickness.

PROCRETE	WATER	SAND/CEMENT
1 Part	1 Part	3:1

## DRYING

Allow a minimum of 24 hours to dry, allow longer in adverse weather conditions. Drying times may vary depending on application and is dependent on substrate porosity, ambient temperature and relative humidity.

## CLEANING

**MCB<sup>TM</sup> ADMIX-B** can be cleaned up using warm water and detergent prior to drying.

## STORING

When **MCB<sup>TM</sup> ADMIX-B** is stored in its original unopened package in a dry area off the ground at a temperature of 23°C and a relative humidity of 60%, it should be usable for approximately 12 months.

## HANDLING

CTA<sup>TM</sup> supports best practice in material handling: Gloves, mask & protective clothing should be worn. For further info refer to product SAFETY DATA SHEET.

## PACK SIZE

20 L and 5L plastic containers

## LIMITATIONS

- **MCB<sup>TM</sup> ADMIX-B** is not suitable for use as a primer.
- **MCB<sup>TM</sup> ADMIX-B** is not suitable as a bonding agent over non-porous substrates including, steel trowel finish floors or dense, non porous concrete, metal, plastic, glass or other similar impervious substrates.
- Do not apply onto permanently wet or damp substrates.
- Do not apply in temperatures below 5°C and above 35°C and under hot and windy conditions.
- Do not allow the product to freeze.
- Contact CTA<sup>TM</sup> Technical Department for further information.

## WARRANTY

Construction Technologies Australia Pty Ltd (CTA<sup>TM</sup>) warrants its products for a period of twelve (12) years from the date of sale. Visit [www.ctaust.com.au](http://www.ctaust.com.au) to view the full terms and conditions of this warranty.

### NEW SOUTH WALES

2 Prime Drive  
Seven Hills NSW 2147  
t 02 9674 1004 f 02 9674 2002

### QUEENSLAND

70 Parker Court Pinkenba QLD 4008  
t 07 3633 9222 f 07 3633 8200

### VICTORIA / TAS

33 Fiveways Boulevard  
Keysborough VIC 3173  
t 03 9797 0600 f 03 9797 0666

### SOUTH AUSTRALIA / NT

28 Kenworth Road Gepps Cross SA 5094  
t 08 8162 9055 f 08 8162 9099

### WESTERN AUSTRALIA

61 Bushland Ridge  
Bibra Lake WA 6155  
t 08 9456 3655 f 08 9456 3644

### NEW ZEALAND

85-91 Patiki Road  
Avondale Auckland 1026  
t 0800 745 269 f 0800 745 232